

# Material Data

Data listed below are only for reference. Data can be adjusted in order to meet special requirement

	IS 900	IS 930
Thickness	6mm	6mm
Wavelength	%T	%T
200	0.00	0.00
280	0.00	0.00
300	0.00	0.00
320	0.00	0.00
360	0.00	0.00
380	0.00	0.00
400	0.00	0.00
420	0.00	0.00
460	0.00	0.00
480	0.00	0.00
500	0.00	0.00
520	0.00	0.00
560	0.00	0.00
580	0.00	0.00
600	0.00	0.00
620	0.00	0.00
640	0.00	0.00
680	0.00	0.00
700	0.00	0.00
720	0.00	0.00
740	0.00	0.00
760	0.00	0.00
780	0.00	0.00
800	7.10	0.00
840	20.40	0.00
880	37.00	11.30
920	53.40	40.60
960	67.50	68.30
1000	77.80	80.90
1100	83.80	85.00
1200	85.40	85.00
1300	86.50	85.00
1400	86.60	85.00
1500	86.70	84.50