

橙色玻璃—OS 565

物理化学参数


| Nd | ρ (g/cm ³) | Thermal | | Chemical | |
|-------|--------------------------------|---------|--------|----------|----|
| | | Tg(°C) | Ts(°C) | DA | DW |
| 1.523 | 2.64 | 527 | 605 | 3 | 2 |

色度

| A[2856K] | | | D65 | | |
|----------|-------|------|-------|-------|------|
| x | y | Y | x | y | Y |
| 0.622 | 0.377 | 51.6 | 0.605 | 0.395 | 36.7 |

光谱要求

| Thickness | λ_t (nm) | λ_p (nm) | T λ_p (%) |
|-----------|------------------|------------------|-------------------|
| 2mm | 560±10 | 650 | >90 |



The wavelength at T= 45%

Limit of passband

Transmittance specified to be λ_p (nm)

***We could get any value of "λt" required
if you could not find the type listed above***

光谱曲线

