

Material Data

Data listed below are only for reference. Data can be adjusted in order to meet special requirement

	UC 220	UC 240	UC 260	UC 280	UC 300
Thickness	2mm	2mm	2mm	2mm	2mm
Wavelength	%T	%T	%T	%T	%T
200	32.50	0.00	0.00	0.00	0.00
220	43.30	27.10	0.00	0.00	0.00
240	68.90	47.40	20.90	2.70	0.00
250	74.70	56.50	32.40	8.30	0.00
260	80.50	65.50	42.00	12.10	0.00
280	87.20	78.70	71.90	43.70	0.60
300	89.80	86.40	84.90	75.30	40.40
320	90.70	89.80	90.60	86.50	75.90
340	90.70	90.70	90.40	89.80	88.30
350	90.70	90.70	90.60	90.20	89.40
360	90.70	90.70	90.60	90.60	90.20
380	90.70	90.70	90.60	90.60	90.60
400	90.70	90.70	90.60	90.60	90.90
420	90.70	90.70	90.60	90.60	90.90
440	90.70	90.70	90.60	90.60	90.90
450	90.70	90.70	90.60	90.60	90.90
460	90.70	90.70	90.60	90.60	90.90
480	90.70	90.70	90.60	90.60	90.90
500	90.70	90.70	90.60	90.60	90.90
520	90.70	90.70	90.60	90.60	90.90
540	90.70	90.70	90.60	90.60	90.90
550	90.70	90.70	90.60	90.60	90.90
560	90.70	90.70	90.60	90.60	90.90
580	90.70	90.70	90.60	90.60	90.90
600	90.70	90.70	90.60	90.60	90.90
620	90.70	90.70	90.60	90.60	90.90
640	90.70	90.70	90.60	90.60	90.90
650	90.70	90.70	90.60	90.60	90.90
660	90.70	90.70	90.60	90.60	90.90
680	90.70	90.70	90.60	90.60	90.90
700	90.70	90.70	90.60	90.60	90.90
720	90.70	90.70	90.60	90.60	90.90
740	90.70	90.70	90.60	90.60	90.90
750	90.70	90.70	90.60	90.60	90.90
760	90.70	90.70	90.60	90.60	90.90
780	90.70	90.70	90.60	90.60	90.90
800	90.70	90.70	90.60	90.60	90.90
840	90.70	90.70	90.60	90.60	90.90
880	90.70	90.70	90.60	90.60	90.90
920	90.70	90.70	90.60	90.60	90.90
960	90.70	90.70	90.60	90.60	90.90
1000	90.70	90.70	90.60	90.60	90.90